

Article No.	1980
EAN-Code	4251744519808
Title	Eur. Cherry worktop FJ A/C 40x5000x1255 bulk FSC
Thickness in mm	40
Length in mm	5000
Width in mm	1255
Type of wood	Kirsche ged.
Quality	A/C
Type of lamella	kgz
Width of lamella	ca. 39-43mm fix
Packaging / Foiling	paketw. 5 Stk/Paket
Description	Solid wood panel for kitchen worktop, Europ. Cherry steamed, Quality A/C (topside no sap, color sorted, no knots / sap only on bottom side), FJ fingerjointed, lamella widths 39-43mm fix, lengths of lamellas 180-400mm, m.c. 8+/-2%, glued D4-EN 204, sanded 100 grit, ends trimmed, FSC 100%, bulk foiled, packed on 4 beams, size 40x5000x1255mm
Wood moisture	At the end of production, the wood moisture is approx. 8 +/- 2%, which corresponds to the equilibrium moisture when used in closed rooms with a healthy living climate of 20°C / 55% humidity
Gluing	All solid wood panels / glued wood panels are glued formaldehyde-free using tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in accordance with DIN/EN 204. Areas of application for these PVAc glues (=white glues) are indoor areas with frequent short-term exposure to runoff water or condensation and/or exposure to high humidity. As well as outdoor areas, but protected from the weather. The glue content for solid wood panels is only approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, chipboards are usually bound to formaldehyde resin and have a glue content of up to 10%). With D3 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/1 (dry area according to EN 13986) can be achieved. With D4 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved.
DIN standard	All LARBON® solid wood panels clearly exceed the necessary specifications of the European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2 (optical appearance classes).