

| Article No.         | 2009  |
|---------------------|---|
| EAN-Code            | 4251744520095   |
| Title               | Oak Live Edge table EGP Rustic 40x2000x1000 foiled                                  |
| Thickness in mm     | 720   |
| Length in mm        | 1500  |
| Width in mm         | 755   |
| Type of wood        | Tischbein Doppel X Matrix   |
| Quality             | Tisch Doppel X  |
| Type of lamella     | schwarz RAL 9005  |
| Width of lamella    |   |
| Packaging / Foiling | im Karton verpackt  |
| Description         | Solid wood panel for table top, Europ. Oak, real "Live Edge", Quality RUSTIC        |
|                     | (topside Rustik, no sap / sap only on bottom side C, both sides knots filled black, |
|                     | EGP long lamella, random widths of lamella, m.c. 8+/-2%, glued D4-EN 204,           |
|                     | sanded 100 grit, FSC 100%, single foiled, size 40x2000x1000mm                       |
| Wood moisture       | At the end of production, the wood moisture is approx. 8 +/- 2%, which              |
|                     | corresponds to the equilibrium moisture when used in closed rooms with a            |
|                     | healthy living climate of 20°C / 55% humidity                                       |
| Gluing              | All solid wood panels / glued wood panels are glued formaldehyde-free using         |
|                     | tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in   |
|                     | accordance with DIN/EN 204. Areas of application for these PVAc glues (=white       |
|                     | glues) are indoor areas with frequent short-term exposure to runoff water or        |
|                     | condensation and/or exposure to high humidity. As well as outdoor areas, but        |
|                     | protected from the weather. The glue content for solid wood panels is only          |
|                     | approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast,      |
|                     | chipboards are usually bound to formaldehyde resin and have a glue content of       |
|                     | up to 10%). With D3 gluing, only the technical class of solid wood panels           |
|                     | according to EN 13353 of SWP/1 (dry area according to EN 13986) can be              |
|                     | achieved. With D4 gluing, only the technical class of solid wood panels according   |
|                     | to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved.              |
| DIN standard        | All LARBON ® solid wood panels clearly exceed the necessary specifications of the   |
|                     | European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2         |
|                     | (optical appearance classes).   |