

|                            |   |
|----------------------------|---|
| <b>Article No.</b>         | 2206  |
| <b>EAN-Code</b>            | 4251744522068   |
| <b>Title</b>               | Oak veneered panel A/B EGP foiled 40x2200x1210  |
| <b>Thickness in mm</b>     | 40  |
| <b>Length in mm</b>        | 2200  |
| <b>Width in mm</b>         | 1210  |
| <b>Type of wood</b>        | Eiche Möbelbauplatte furniert   |
| <b>Quality</b>             | A/B Deckfurniere  |
| <b>Type of lamella</b>     | furniert DL   |
| <b>Width of lamella</b>    | beids. furniert 0,6mm x 80-200mm  |
| <b>Packaging / Foiling</b> | einzelni foliert  |
| <b>Description</b>         | <p>Solid Wood panels, Oak veneered, Oak FJ base panel 18,8mm veneered both sides 0,6mm quarter cut mismatched, A/B (both sides no sap / no knots, topside color sorted), widths of topside veneer ca. 80-200mm random, glued D4-EN 204, sanded grit 100, single foiled, size 40x2200x1210mm, 20 pcs per pallet</p> <p>A-side.<br/>European Oak Quarter cut veneer A-quality, mismatched spliced ( solid wood appearance ), No sapwood allowed, no open defects, small/closed solid pin knots allowed, relatively uniform color.</p> <p>B-side.<br/>European Oak veneer, mix of quarter &amp; crown (blumig) mismatched spliced ( solid wood appearance ), No sapwood allowed, no open defects, more color differences allowed, some closed dark knots allowed.</p>  |
| <b>Wood moisture</b>       | At the end of production, the wood moisture is approx. 8 +/- 2%, which corresponds to the equilibrium moisture when used in closed rooms with a healthy living climate of 20°C / 55% humidity   |
| <b>Gluing</b>              | All solid wood panels / glued wood panels are glued formaldehyde-free using tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in accordance with DIN/EN 204. Areas of application for these PVAc glues (=white glues) are indoor areas with frequent short-term exposure to runoff water or condensation and/or exposure to high humidity. As well as outdoor areas, but protected from the weather. The glue content for solid wood panels is only approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, chipboards are usually bound to formaldehyde resin and have a glue content of up to 10%). With D3 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/1 (dry area according to EN 13986) can be achieved. With D4 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved. |

|                     |  |
|---------------------|--|
| <b>DIN standard</b> | All LARBON <sup>®</sup> solid wood panels clearly exceed the necessary specifications of the European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2 (optical appearance classes). |
|---------------------|--|