

|                            |   |
|----------------------------|---|
| <b>Article No.</b>         | 2235  |
| <b>EAN-Code</b>            | 4251744522358   |
| <b>Title</b>               | Pine EGP long lamella A/A 30x1000x620mm   |
| <b>Thickness in mm</b>     | 30  |
| <b>Length in mm</b>        | 1000  |
| <b>Width in mm</b>         | 620   |
| <b>Type of wood</b>        | Kiefer  |
| <b>Quality</b>             | A/A astfrei   |
| <b>Type of lamella</b>     | DL  |
| <b>Width of lamella</b>    | ca. 40-45mm fix   |
| <b>Packaging / Foiling</b> |   |
| <b>Description</b>         |   |
| <b>Wood moisture</b>       | At the end of production, the wood moisture is approx. 8 +/- 2%, which corresponds to the equilibrium moisture when used in closed rooms with a healthy living climate of 20°C / 55% humidity   |
| <b>Gluing</b>              | All solid wood panels / glued wood panels are glued formaldehyde-free using tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in accordance with DIN/EN 204. Areas of application for these PVAc glues (=white glues) are indoor areas with frequent short-term exposure to runoff water or condensation and/or exposure to high humidity. As well as outdoor areas, but protected from the weather. The glue content for solid wood panels is only approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, chipboards are usually bound to formaldehyde resin and have a glue content of up to 10%). With D3 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/1 (dry area according to EN 13986) can be achieved. With D4 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved. |
| <b>DIN standard</b>        | All LARBON <sup>®</sup> solid wood panels clearly exceed the necessary specifications of the European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2 (optical appearance classes).  |