

Article No.	2542
EAN-Code	4251744525427
Title	Eur. Oak EGP Rustik B/B (2x20mm) 40x1400x650mm
Thickness in mm	40
Length in mm	1400
Width in mm	650
Type of wood	Wildeiche Treppenst. 2-S
Quality	Asteiche
Type of lamella	DL 2-schicht
Width of lamella	ca. 50mm fix
Packaging / Foiling	neu
Description	Solid wood panel for stairs, Europ. Oak, 2-layer (20+20mm), first and last lamella 1-layer, Quality Rustik B/B (both sides no sap, only small knots filled black), EGP long lamella, lamella widths ca. 45-50mm fix, m.c. 8+/-2%, glued D4-EN 204, sanded 100 grit, DET double end trimmed, bulk foiled, size 40x1400x650mm
Wood moisture	At the end of production, the wood moisture is approx. 8 +/- 2%, which corresponds to the equilibrium moisture when used in closed rooms with a healthy living climate of 20°C / 55% humidity
Gluing	All solid wood panels / glued wood panels are glued formaldehyde-free using tested German brand glues (e.g. Jowatt, Kleiberit) of stress classes D3 and D4 in accordance with DIN/EN 204. Areas of application for these PVAc glues (=white glues) are indoor areas with frequent short-term exposure to runoff water or condensation and/or exposure to high humidity. As well as outdoor areas, but protected from the weather. The glue content for solid wood panels is only approx. 0.1%. The PVA glues used do not release any formaldehyde (in contrast, chipboards are usually bound to formaldehyde resin and have a glue content of up to 10%). With D3 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/1 (dry area according to EN 13986) can be achieved. With D4 gluing, only the technical class of solid wood panels according to EN 13353 of SWP/2 (wet area according to EN 13986) can be achieved.
DIN standard	All LARBON® solid wood panels clearly exceed the necessary specifications of the European standards DIN EN 13353 (technical requirements) and DIN EN 13017-2 (optical appearance classes).